

# **KW Plastics**

### PCR TECHNICAL DATA SHEET

279 Pike County Lake Rd Troy, AL 36081 | 334.566.1563 | 800.633.8744 | kwplastics.com

## KWR101-150

Natural Homopolymer High Density Polyethylene Post-Consumer Resin Blow Molding and Extrusion

PROPERTY	NOMINAL VALUES
FNOFENTI	NOMINAL VALUES

Melt Flow ASTM-D1238 0.60 g/10 minutes Specific Gravity ASTM-D792 0.960 g/ml Notched Izod Impact ASTM-D256, A non break Flexural Modulus ASTM-D790 165,000 psi Tensile Yield Strength ASTM-D638 3,700 psi KW-MA01 Moisture 0.02% max.

**COLOR** 

L Hunter Scale 68

**REGULATORY** 

CONEG Compliant & Certified <100 ppm total
REACH/ SVHC Compliant
Flammability,
0.38 mm min. thickness UL94HB

#### **CHARACTERISTICS**

Natural color, high stiffness, good impact resistance.

#### **QUALITY**

ISO 9001: 2008 registered, ISO/ IEC 17025: 2005 accredited laboratories, C.O.A. on every lot.

NOTE: While this information is presented in good faith and believed to be accurate, KW does not guarantee satisfactory results from reliance upon such information and disclaims all liability for any loss or damage arising out of its use. No information contained herein is to be construed as a recommendation to use this product in conflict with any patent.