

KW Plastics TECHNICAL DATA SHEET

279 Pike County Lake Rd Troy, AL 36081 | 334.566.1563 | 800.633.8744 | kwplastics.com

KWR105M4

Copolymer High Density Polyethylene Resin

	NOMINAL VALUES
ASTM-D1238	4 g/10 minutes
ASTM-D792	0.945 g/ml
ASTM-D256, A	non break
ASTM-D790	120,000 psi
ASTM-D638	2,600 psi
KW-MA01	0.07%
D5576	15%
	ASTM-D792 ASTM-D256, A ASTM-D790 ASTM-D638 KW-MA01

REGULATORY

CONEG	\checkmark
REACH/ SVHC	\checkmark
PROPOSITION 65	\checkmark

CHARACTERISTICS Exceptional toughness. Available as mixed color and pre-colored black.

APPLICATIONS

Injection molding

QUALITY

ISO 9001: 2015 registered, ISO/ IEC 17025: 2005 accredited laboratories, C.O.A. on every lot.

NOTE: While this information is presented in good faith and believed to be accurate, KW does not guarantee satisfactory results from reliance upon such information and disclaims all liability for any loss or damage arising out of its use. No information contained herein is to be construed as a recommendation to use this product in conflict with any patent. KW Plastics may add minerals, modifiers, color concentrates and other material to enhance the visual and physical performance of its resins.