

Carlsbad 12"x24"



ICE



GREY



SAND



WALNUT

Carlsbad 12"x24"



Dry - Pressed Ceramic Tiles ISO 13006 : 2012 Annex G - UNI EN 14411 : 2012 Annex G - Bla GL



ICE 12"x24"



GREY 12"x24"



SAND 12"x24"











WALNUT 12"x24"

PACKING AND WEIGHT

SIZE	PIECES / CARTON	SF/CARTON	CARTON/PALLET	SF/PALLET	SF/PIECE	LBS/CARTON
12"x24"	6	11.6	40	464.8	1.9	53.5

TECHNICAL FEATURES

	STANDARD	VALUE
	UNI EN ISO 10545/2	± 0,26% / ± 1,5mm
 Flatness	ASTM C485 Warpage Calibrated ± 0,75% (max ± 0,09 in)	-
	Rectified ± 0,40% (max ± 0,05 in-size ≤ 60cm) (max ± 0,07 in-size > 60cm)	± 0,25% (max ± 0,05 in-size ≤ 60cm) (max ± 0,07 in-size > 60cm)
 Water absorption - Average value expressed in %	UNI EN ISO 10545/3 ≤ 0,5 % ASTM C373	Compliant
 Modulus of rupture	UNI EN ISO 10545/4	≥ 50 N/mm ²
 Breaking strength	UNI EN ISO 10545/4 ASTM C648	≥ 2000 N 700 LBS
 Frost resistance	UNI EN ISO 10545/12 ASTM C1026	Compliant Unaffected
 Chemical resistance to high and low acid and basic concentrations	UNI EN ISO 10545/13 ASTM C-650	GA - GLA - GHA Unaffected
 Stain resistance	UNI EN ISO 10545/14 CTI 81-7D	5 No Evident Variation
	DIN 51130	Naturale R10 Lappato R10 Strutturato R11
 Slip resistance	DWIN 51097	C (A+B+C) B (A+B) C (A+B+C)
	ANSI A 137.1- 2012 DCOF (Section 9.6)	Dry: 0,69* Wet: 0,59* Dry: 0,67* Wet: 0,46* Dry: 0,74** Wet: 0,72**
	B.C.R.A.	≥ 0,40 ≥ 0,40 ≥ 0,40

* Values obtained with certificate n° 20130041.
Date 02/12/2013.

** Values obtained with certificate n° 20130041.
Date 03/18/2013.

For further information on technical specifications,
please consult our up-dated general catalogue.



16610 Gale Ave. • Industry, CA 91745
Tel. (626) 961-0051 • Fax (626) 336-2217